



Norland Optical Adhesive 136

Norland Optical Adhesive 136 is clear liquid adhesive that will cure when exposed long wavelength ultraviolet light. NOA 136 is recommended for bonding for glass to glass. Adhesion is also good to cellulose acetate butyrate. NOA 136 is cured by ultraviolet or visible light between 315 to 450 nm. Full cure requires 6 Joules/cm². The adhesive exhibits oxygen inhibition when used as a coating. To overcome this the adhesive must be cured under an inert atmosphere, such as nitrogen.

Typical Properties of NOA 136

Viscosity @ 25C	160 cps
Refractive Index of cured Polymer	1.36
Color	Clear
Modulus (psi)	923
Tensile (psi)	393
Elongation at Failure	58
Shore D	20
Temperature Range	-15 C to 90° C

Keep NOA 136 in a cool (5-22 ° C) dark place. If refrigerated, allow the adhesive to come to room temperature before using.

Care should be taken in handling the this material. The material Safety Data Sheet should be read for this product. Prolonged contact with skin should be avoided and affected areas should be washed thoroughly with copious amounts of soap and water. If adhesive gets into eyes, flush with water for 15 minutes and seek medical attention.

Spectral Transmission of NOA 136

