



amstechnologies
where technologies meet solutions

info@amstechnologies.com
www.amstechnologies-webshop.com

Contact us



GHOPTICS
光皓光学

GH Optics (Jiangsu) Co., LTD.





Precision Molded Glass Aspheric Lenses

Lens Code	EFL	WD	NA	CA	OD	DW
	mm	mm		mm	mm	nm
LE0850	0.80	0.40	0.47	0.71	3.000	940
LD1560	1.50	0.80	0.58	1.60	2.400	780
LE1840	1.80	1.10	0.37	1.35	3.000	1550
LG2560	2.50	1.62	0.60	3.04	4.000	488
LF2570	2.50	1.55	0.66	3.30	4.000	405
LE2850	2.80	2.70/7.10	0.52/0.26	4.12/3.76	4.700	980
LE2860	2.80	1.50	0.64	3.60	4.000	830
LE2861	2.80	2.16	0.55	3.60	4.500	830
LD3170	3.10	1.80	0.68	5.00	6.325	830
LD4060	4.00	2.68	0.64	5.10	6.325	685
LG4060	4.00	2.40	0.60	4.80	6.325	408
LD4530	4.50	3.50	0.30	2.70	3.000	635
LD4540	4.50	2.20	0.40	3.70	4.700	980
LE4560	4.50	3.10	0.55	5.07	6.325	780
LD4650	4.60	2.70	0.54	4.80	6.000	655
LD5020	5.00	4.37	0.15	1.60	2.000	1550
LD5320	5.30	4.19	0.24	2.50	3.000	975
LD5560	5.50	3.70	0.58	6.00	7.200	635
LD6020	6.00	4.90	0.21	2.50	3.000	1550
LD6230	6.20	4.10	0.30	3.70	4.700	635
LE6240	6.20	3.50	0.40	5.00	7.200	780
LD6740	6.70	4.90	0.44	5.75	6.650	515
LE7530	7.50	5.80	0.30	4.54	6.510	780
LD8050	8.00	5.90	0.50	8.00	9.936	780
LD9630	9.60	8.10	0.27	5.20	6.325	635
LD9930	9.90	8.40	0.27	5.20	6.335	650
LDA050	10.00	7.80	0.51	10.00	11.000	635
LDA130	11.00	7.90	0.25	5.50	7.200	635
LDA320	13.00	11.60	0.20	5.20	6.325	633
LDA520	15.30	14.00	0.16	5.00	6.500	785
LDA820	18.40	17.10	0.15	5.50	6.500	785
LDB210	22.00	20.41	0.13	5.50	6.325	670

All the glass material we selected is according to RoHS requirements.

Standard Coatings		
VA	380~700nm	$R_{avg} \leq 0.5\%$
VB	600~1100nm	$R_{avg} \leq 0.6\%$
VC	1050~1650nm	$R_{avg} \leq 0.5\%$
VQ	1300~1700nm	$R_{avg} \leq 0.25\%$

Glass Types	
LD	D-Zk3
LE	D-ZLaF52La
LF	L-LAL12
LG	D-LaK6



Distributor



amstechnologies

where technologies meet solutions

info@amstechnologies.com
www.amstechnologies-webshop.com

Contact us 